

Base Preparation for Slabs on Grade

Problems and Practice #2

Base preparation, including the subgrade and subbase, is an important consideration in the long-term performance of the decorative concrete slab. Poor base preparation can result in settlement, varying concrete slab thickness, and poor drainage, which can lead to cracking. Unless the subcontractor has a specific item in his contract for base preparation, the general contractor or builder is responsible for providing a satisfactory base. Even if the decorative contractor is not responsible for the base preparation they have an obligation to address unsatisfactory conditions to the accountable party prior to performing their contractual work.

ACI 302.1R-04 “Guide for Floor and Slab Construction” provides recommendations for constructing a proper base. These recommendations and others include:

- In-place density of the subgrade, subbase and base should be at least the minimum required by specification, or not less than 90% Proctor.
- Backfill around walls or trenches should be placed in layers less than 8-in. thick and compacted to meet density specifications.
- Base should be dry at time of concrete placement and free of frost, standing water, and soft or muddy spots.
- Base material should be a compactible, easy to trim, granular fill (not sand) that will remain stable and support construction traffic.
- Base elevation tolerance should be within \pm 1/2 in. of the required elevation.

- Proof-rolling with a loaded ready mix truck should not result in any surface depression greater than 1/2 in.

In commercial construction, an independent soils testing laboratory usually confirms the base preparations are adequate. However decorative concrete is sometimes a part of residential construction, including remodel or owner work, and new construction where the homebuilder is the general contractor and is responsible for the subgrade, subbase, and base preparation. Performance issues related to a subgrade or base that the decorative concrete contractor has not prepared are the responsibility of the general contractor. The decorative concrete contractor will notify the general contractor or owner of the lack of adequate base preparation and its consequences when poor conditions exist and proceed only when given owner approval.

Decorative concrete contractors will work with Owners and Architects in developing specifications for proper base preparation. If you have any questions, contact your ASCC concrete contractor or contact the ASCC Decorative Concrete Hotline at (888) 483-5288.



2025 S. Brentwood Blvd. Suite 105 ■ St. Louis, MO 63144
Telephone: 314-962-0210 ■ Website: www.ascconline.org
Toll Free: 866-788-2722 ■ E-mail: ascc@ascconline.org